

**CHC06-18 醇酸带锈防锈漆****CHC06-18 Alkyd Surface Tolerant Antirust Paint**

产品特性 Characteristics	能在冬季或低温下快速干燥; Quick drying in winter or at low temperature 极好的防锈和阻锈性能; Excellent rust prevention and resistance 对生锈表面有良好的附着性; Good adhesion to the rusty surface 良好的施工性能; Good workability 与各种面漆有良好的配套性。 Good compatibility with all kinds of top coats	
产品用途 Uses	主要用于钢铁设施的维修, 亦可用于大型钢结构、钢铁设施、设备、管道防腐用底漆。 For maintenance of steel facilities; or as anticorrosive primer for the large-scale steel structures, facilities, equipment and pipelines.	
颜色 Color	棕黄 Brownish yellow	
施工条件 Application method	无气喷涂 airless spray 喷嘴尺寸 nozzle tip 压力 nozzle pressure 稀释比率 thinning ratio	推荐 recommended 0.4~0.5mm 0.4~0.5mm 100~150kg/cm ² 100~150kg/cm ² 0~5% (重量比) 0~5% (by weight)
	适用于无气喷涂、空气喷涂、刷涂及辊涂 May be applied by airless spray, air spray, brush, or roller.	
稀释剂 Thinner	醇酸稀释剂 Alkyd Thinner	
混合比率 Mixing rate	单组分 One-pack	
涂装膜厚 Film thickness	干膜: 30μm/道 湿膜: 60μm/道 Dry film thickness:30μm/coat Wet film thickness:60μm/coat	
固体含量 Solid content	60%	



比重 Specific gravity	1.45			
涂覆率 Spreading rate	理论值 : 0.09kg/m ² /30μm Theoretical: 0.09kg/m ² /30μm	0.067L/m ² /30μm 0.067L/m ² /30μm		
	实际值 : 与表面处理, 外界环境, 施工方法等多种因素有关。 Practical: varies depending on the surface treatment, environment and application methods.			
干燥时间 Drying time	温度℃ temperature	10	20	30
	指触干燥 hrs dry to touch	1.5	1	0.5
	半硬干燥 hrs dry hard	8	6	4
涂装间隔 Coating interval	Min. 最小 (hrs) Min. (hrs)	15	10	6
	Max. 最大 (hrs) Max. (hrs)	—	—	—
储存期限 Shelf life	一年 12 months			
包装规格 Package	20 公斤/桶 20 kg/barrel			
表面处理 Surface preparation	用手动或电动工具除去松动氧化皮, 可以有毛锈, 但毛锈厚度在 10 微米以下。 Remove the loose scale with manual or power tools, but the un-removable scale of which film thickness is less than 10μm is allowed.			
适用底材 Compatible substrate	裸钢或旧漆膜 Bare Steel or old paint film			
适用上涂 Top coat	醇酸面漆或参照我公司配套 Alkyd Finish, or reference to our coating system			
安全注意事项 Safety Precautions	任何油漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛, 应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical attention. 保证良好的通风。 Assure well-ventilated working place. 小心火灾或爆炸。 Take precautions of the risks of fire or explosion.			



现场遵守一切健康安全规定。
Observe all health and safety regulations on site.

提 醒 注 意
Declaration

本说明书所提供信息均为目前我方所掌握最全面正确的资料，鉴于产品使用条件非我方所能控制，此中信息不含担保，即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展，此中所有信息均以我方确认为准。

The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.
